PROCEEDINGS OF SPIE

SPIDigitalLibrary.org/conference-proceedings-of-spie

Schematic representations for teaching the procedure of optical amplification in fiber amplifiers

Cüneyt Berkdemir, Sedat Özsoy

Cüneyt Berkdemir, Sedat Özsoy, "Schematic representations for teaching the procedure of optical amplification in fiber amplifiers," Proc. SPIE 9664, Ninth International Topical Meeting on Education and Training in Optics and Photonics, 966417 (24 October 2005); doi: 10.1117/12.2207767

SPIE.

Event: Ninth International Topical Meeting on Education and Training in Optics and Photonics, 2005, Marseille, France

Ref ETOP083

Schematic representations for teaching the procedure of optical amplification in fiber amplifiers

Cüneyt Berkdemir (OSA Member) and Sedat Özsoy

Department of Physics, Faculty of Arts and Sciences, Erciyes University, Kayseri, Turkey, 38039, berkdemir@erciyes.edu.tr and ozsoys@erciyes.edu.tr

Abstract

We present the schematic representations for teaching the procedure of optical amplification in erbium and praseodymium doped fiber amplifiers by using rate equations models. The behaviour of these types of amplifiers is the same as three (for erbium ion) and four (for praseodymium ion) levels atomic systems, respectively. Most of the important characteristics of these amplifiers can be obtained from these simple models and their underlying assumptions. Hence, we can make use of these approaches for teaching the purposes of procedures in fiber amplifiers. For this aim, the gain performances of Er^{3+} and Pr^{3+} -doped fiber amplifiers are investigated at the educational level, using the temperature-dependent rate equation model.

Summary

1- Introduction

Fiber optic technology has been advancing at a surprising pace during the last three decades. It was about fifteen years ago that researchers showed the great potential of optical fiber doped with the rare-earth elements such as erbium and praseodymium, for application in long haul communications. Optical amplifiers have been successfully incorporated in the field of fiber communication, accelerating the rate at which optical links are being deployed over the continents and the transoceanics. Today, this technology is fast becoming a major part of optical communications infrastructure in many countries around the world [1, 2]. Therefore, in order to learn this technology at university level, we need to understand the procedure of optical amplification in fiber amplifiers from basic to advance. From this point of view, the education and training programs will make easy to understand the procedure of optical amplification in fiber amplifiers.

2- Schematic Representations of Amplification

This work will enable us to understand the basic physical concepts underlying three and four level fiber amplifiers and obtaining the signal gain of amplifiers by using rate equation models. Figure 1 shows the schematic representations of the energy levels and amplifications mechanism for Er^{3+} (left hand side of picture) and Pr^{3+} (right hand side of picture) ions doped in glass hosts.

Figure 1: Energy levels and amplification mechanism for Er³⁺ (left hand side of picture) and Pr³⁺ (right hand side of picture)-ions in glass hosts.

The energies and populations of three and four level amplifiers can be described by $E_0, E_1, E_2 (= E_{21} + E_{22}), E_3$ and $N_0, N_1, N_2 (= N_{21} + N_{22}), N_3$, respectively, for the thermal equilibrium. By definition, levels 0 and 1 are the lowest or ground state, level 2 is the metastable state, and level 3 is the pump level. The stimulated transition probability R_p is the probability of exciting the ion from level 1 to level 3 for erbium, and from level 0 to level 3 for praseodymium by pumping, and R_s will be referred to the stimulated transition probability between E_2 and E_1 .

$$\begin{aligned} \frac{dN_3}{dt} &= R_p (N_1 - N_3) - \gamma_{32}^{NR} N_3, \\ \frac{dN_2}{dt} &= -R_s (N_2 - N_1) - \gamma_{21} N_2 + \gamma_{32}^{NR} N_3, \\ \frac{dN_1}{dt} &= -R_p (N_1 - N_3) + \gamma_{21} N_2 + R_s (N_2 - N_1), \\ \frac{dN_0}{dt} &= R_p N_3 - R_p N_0 - R_{0s} N_0 + \gamma_{10} N_1. \end{aligned}$$

Let us now consider the steady-state situation, where the populations are time invariant, i.e., $dN_i/dt = 0$ ($i = 0, 1, 2, 3$);

$$N_2 = N \frac{R_p + R_s}{R_p(1 + 2\beta) + R_s(2 + \beta) + \gamma_{21}}, \quad N_1 = N \frac{R_p\beta + R_s + \gamma_{21}}{R_p(1 + 2\beta) + R_s(2 + \beta) + \gamma_{21}}; \quad \text{for Er}^{3+}\text{-doped fiber,}$$

$$N_{22} = N \frac{R_p}{\gamma_{21} + R_p(1 + 1/\beta) + R_{2s}}, \quad N_0 = N \frac{\gamma_{21} + S_{2s}}{\gamma_{21} + R_p(1 + 1/\beta) + S_{2s}}; \quad \text{for Pr}^{3+}\text{-doped fiber.}$$

Here, β quantity is involved in the issue because of the E_2 and E_3 levels of Er^{3+} and the E_{22} and E_{21} levels of Pr^{3+} -doped fibers are very closely spaced according to the

Boltzmann's population relation $N_m/N_{m-1} = e^{-\Delta E_m/k_B T}$
 $(\Delta E_m = E_m - E_{m-1}, k_B = 1.38 \times 10^{-23} \text{ J/K})$. We consider an absorbing medium for the description of the signal gain. The signal gain is given by $G = \exp[\Gamma_s (\sigma_{21} N_2 - \sigma_{12} N_1) L]$ for Er^{3+} -doped fiber [3] and by $G = \exp[\Gamma_s \sigma_{2s} N_{22} L]$ for Pr^{3+} -doped fiber amplifiers [1]. Here, L denotes the fiber amplifier length and the other parameters represent the standard fiber parameters.

3- Conclusions

We have introduced simple schematic representations for energy levels and amplification mechanisms, and used the basic rate equation models, including the temperature effect to obtain the signal gain of the erbium and praseodymium-doped fiber amplifiers at university level. In addition, we have shown the possibility of deriving an analytical solution of the rate equations in some practical temperature ranges to understand the gain performance of both fiber amplifiers.

Acknowledgment

This study is supported by Scientific Research Projects Council (SRPC) of Erciyes University under Grant No FBA-04-01.

References

- 1- P.C. Becker, N. Olsson, J. Simpson, Erbium-Doped Fiber Amplifiers: Fundamentals and Technology, Academic Press, San Diego, (Copyright by Lucent Technologies) 1999.
- 2- K. Amano and Y. Iwamoto, Optical Fiber Submarine Cable System, Journal of Lightwave Technology., vol. 8, no. 4, 595, (1990).
- 3- C. Berkdemir and S. Özsoy, [The temperature dependent performance analysis of EDFAs pumped at 1480 nm: A more accurate propagation equation](#), Optics Express, 13 (13), 5179, (2005).