Evaluation of marginal gap of lithium disilicate glass ceramic crowns with optical coherence tomography

Wenhao Li
Jingming Liu
Zhenting Zhang

Evaluation of marginal gap of lithium disilicate glass ceramic crowns with optical coherence tomography

Wenhao Li,^a Jingming Liu,^b and Zhenting Zhang^{c,*}

^aPlastic Surgery Hospital, Chinese Academy of Medical Sciences and Peking Union Medical College, Department of Stomatology, Beijing, China

^bBeijing Tong Ren Hospital, Capital Medical University, Department of Stomatology, Beijing, China

^cCapital Medical University School of Stomatology, Department of Prosthodontics, Beijing, China

Abstract. Marginal gap (MG) was the most important factor to evaluate the success of crowns. The study was to assess the MG of lithium disilicate glass ceramic crowns with spectral domain optical coherence tomography (OCT) and stereomicroscopy *in vitro*, and to provide evidence to measure the MG with OCT. Consistency was observed between OCT and stereomicroscopy to measure the MG after cementation. There was no significant difference between the MG of lithium disilicate glass ceramic crowns using OCT and stereomicroscopy (OCT $59.55 \pm 7.22 \mu\text{m}$, stereomicroscope $59.48 \pm 6.53 \mu\text{m}$, $P = 0.736$) after cementation. OCT was a noninvasive diagnostic technique to measure the MG of lithium disilicate glass ceramic crowns. © 2018 Society of Photo-Optical Instrumentation Engineers (SPIE) [DOI: 10.1117/1.JBO.23.3.036001]

Keywords: optical coherence tomography; stereomicroscopy; marginal gap.

Paper 170469SSRR received Jul. 18, 2017; accepted for publication Feb. 7, 2018; published online Mar. 2, 2018.

1 Introduction

Marginal gap (MG) was the most important factor to evaluate the success of crowns.^{1,2} Holmes et al.³ described MG as the horizontal discrepancy from the crown surface and the tooth (Fig. 1). Previous studies had described various methods to measure the MG including direct-view technique, cross-sectioning technique, replica technique, profile projector, digital impression, and microcomputed tomography ($\mu\text{-CT}$). Due to the limitations, those techniques could have a significant impact on the results.^{4–8} It was difficult to identify reference points to measure⁹ and thus led to projection errors,¹⁰ when direct-view technique was applied. While only partial sections of the specimen could be obtained, and might not represent the complete gap of the crown for long-term analysis and comparison of the MG when cross-sectioning technique was applied.^{11,12} It was difficult to detect micron-scale gaps due to the radio-opacity similarity between the adhesive and the air when $\mu\text{-CT}$ was used.¹³ The silicone replication was the only MG measurement method used *in vivo*, but the results were not as accurate as those yielded *in vitro*.¹⁴

Optical coherence tomography (OCT) was a noninvasive diagnostic imaging technique based on the light backscattering of the interior biologic microstructure and material. OCT had been applied in clinic and prospective studies in terms of cardiology, orthopedics, and ophthalmology. OCT used safe light sources to produce time-domain, high-resolution cross-sectional images. Tooth hard tissues and lithium disilicate glass ceramic were good scattering media, so they were suitable substrates for OCT.^{15,16} Tooth restoration interface under direct and indirect resin restorations had been investigated using this technique;^{17–21} however, few data were recorded on evaluation of the MG of a lithium disilicate glass ceramic crown with OCT. This study was to measure the MG of lithium disilicate glass ceramic crowns with OCT and stereomicroscopy technique,

and to provide evidence to measure the MG of lithium disilicate glass ceramic crowns with OCT for clinical requirement.

2 Material and methods

2.1 Specimen Preparation

In this study, 32 extracted human maxillary third molars without cracks, caries, and restorations were selected after obtaining informed consents of the patients. The ceramic crown preparation was free of undercuts, the occlusal surface was reduced 2 mm, the angles were rounded, and the walls were tapered 6 deg to the occlusal surface. The margins were 1-mm wide with chamfer finish line design above the 1.5-mm cemento-enamel junction. A thin layer of titanium dioxide powder was applied to the prepared surface with an aerosol (Cerec powder, Vita Zahnfabrik, Germany). Optical impressions of the prepared teeth were made using the scanner (MD-ID 200, Segma, Korea). The crowns were designed by HyperDent CAD software with luting space and adhesive gap set to 0 μm .⁵ A milling unit (ARUM 5X-200, Segma, Korea) was used for CAM processing of the designed crowns. The lithium disilicate glass ceramic materials (IPS e.max CAD Ivoclar-Vivadent, Liechtenstein) were used to fabricate the crowns. After the completion of the milling process, all the crowns were crystallized in a porcelain furnace (Programat EP 3010, Ivoclar-Vivadent, Liechtenstein). The total etching technique was performed and the crowns were bonded to the teeth with luting (Variolink N, Ivoclar-Vivadent, Liechtenstein) according to the manufacturer's instructions. After one hour of cementation, all specimens were embedded under 2-mm cemento-enamel junction by epoxy resin and stored in deionized water at 37°C for one week. This study was approved by ethics committee at Beijing Tong Ren Hospital, Capital Medical University (Clinical Trials. 2014BJSZR-10).

*Address all correspondence to: Zhenting Zhang, E-mail: LiWHSCI@163.com

Fig. 1 Crown misfit terminology (a) absolute marginal discrepancy and (b) MG.

2.2 Optical Coherence Tomography

A spectral domain OCT system (iVue-100, Optovue) was used in this study. The scan beam wavelength was 840 ± 10 nm with a 26-kHz sweep rate. The axial and lateral resolution of the system was 5 and 15 μm , respectively. A series of A-scans from the crowns to the teeth produced a raw data file (B-scan) with information of backscattered light as well as X , Z coordinates of each point in the scanned area. Backscattered light carrying microstructure information of the specimens was received by the system, and then digitized into time-series data that can be analyzed to reveal the depth information of the subject. The system was capable of creating real-time high-resolution 2-D images by analyzing the frequency components of backscattered light from the specimens.

To ensure the repeatability of the OCT scans for the same specimen, thin lines were drawn on the surface of each crown to assure that specimens were accurately placed at the exact same angle. Before the measurement, the object lens center, marked line on the crown and the tooth long axis were on the same geometric plane, and the object lens center and marked line of restoration were perpendicular to the axis with a special device (Fig. 2). To capture the OCT image, the specimen was positioned along the tooth long axis and rotated 7.5 deg each time. In this manner, 48 serial 2-D sections for each tooth were obtained with gray-scale images. For the data analysis, each of the 48 2-D sections was digitally analyzed using Image J (ver. 1.50i, National Institutes of Health). A customized program was plugged into the ImageJ to facilitate the analysis procedure and identify pixel clusters with higher brightness indicating the MG. The picture was turned to 8-bit. We used the line profile tool to detect the gray value between ceramic and tooth, and used the line selection tool in ImageJ to draw a line along the length of the scale bar in the right side of

Fig. 2 OCT equipment and special device to fix a tooth: we used a special device to locate and turn the teeth and to ensure the repeatability of the OCT scans for the same specimen (left arrow).

the figure as a calibration, draw a horizontal line between enamel and ceramic, and calculate the MG of the crowns using the equation as below.

The equation used to calculate as follows:

$$\text{The marginal gap of the crowns} = a * b/c,$$

where a the distance of the scale bar, b is the horizontal length between enamel and ceramic, and c is the length of the scale bar.

2.3 Stereomicroscopy

Stereomicroscopy was widely used to detect the MG of crowns due to its convenience and briefness. The specimens were positioned along the tooth long axis and rotated 7.5 deg for each image. The object lens center, marked line of restoration, and axis of the tooth were on the same geometric plane, and the object lens center and marked line of restoration were perpendicular to the axis. In this manner, 48 serial 2-D planes were obtained at a magnification level of 60 $\times$ by stereomicroscopy. For the data analysis, the midline of 2-D planes in the series was digitally analyzed using Image J (ver. 1.50i, National Institutes of Health).

2.4 Statistical Analysis

The horizontal discrepancies between the ceramic surface and the tooth in the series of 48 images of each specimen were recorded as MG (Fig. 1). Descriptive statistics were computed for each group with SPSS v19.0. Bland-Altman analysis and paired t test were used to test consistency of MG between stereomicroscopy and OCT. In all evaluations, the p value <0.05 was considered statistically significant.

3 Results

The results showed no significant difference in the MG between OCT and stereomicroscopy (OCT 59.55 ± 7.22 μm , stereomicroscope 59.48 ± 6.53 μm , $p = 0.74$) (Table 1). Bland-Altman methods were used to analyze the correlation between the distribution of the scattered distance of the MG measured by OCT and stereomicroscopy, the degree of variation of the measurement method, and the consistency based on the observed difference between the two measurement methods (Figs. 3 and 4). All the indicators of the results mentioned above were found to be comparable between OCT and stereoscopic microscopy.

4 Discussion

This study evaluated the MG of lithium disilicate glass ceramic crowns using OCT and stereomicroscopy. OCT was identified as

Table 1 The MG with OCT and stereomicroscopy paired t test.

		Pair of differentials		Differential 95% confidence interval		t	df	Sig. (two sides)
		Mean	standard deviation	Lower	Higher			
Mean	standard deviation	standard error						
-0.064	1.06	0.19	-0.44	0.32	-0.34	31		0.736

Fig. 3 Consistency analysis of MG with OCT and stereomicroscopy: Bland-Altman analysis.

Fig. 4 Measure the MG with different methods (a) stereomicroscope and (b) OCT [MG shown (up arrow)]; (a) enamel, (b) luting, and (c) lithium disilicate glass ceramic. (a) MG with stereomicroscope was $66.38\ \mu\text{m}$ and (b) MG with OCT was $66.40\ \mu\text{m}$.

a good method to evaluate MG in this study. This study showed consistency between OCT and stereomicroscopy to measure the MG of lithium disilicate glass ceramic crowns after cementation.

Different measurement methods were used to evaluate the MG among the previous studies. Measurements including direct-view technique, cross-sectioning technique, replica technique, profile projector, digital impression, and μ -CT were used to evaluate the MG and led to the results with significant various methods.^{4–8} Those measurement methods had advantages and disadvantages (Table 2). For technical reasons, silicone replication was the only MG measurement method used in the clinic.

It was difficult to identify reference points measured and results of silicone replication were not as accurate as those methods described above *in vitro*.

Compared with measurement methods described above, OCT was a noninvasive diagnostic imaging technique based on different light backscattering of biological microstructures and materials, which could produce real-time, high-resolution images with a safe light source. To date, OCT has been applied to the fields of ophthalmology, pathology, and vascular biology. Previous studies have found that dental materials and dental tissue can backscatter light very suitable for OCT.^{15,21} Without cutting the specimen or using radioactive material, the OCT can detect the adhesive interface of the tooth directly repaired.^{17–21} Turkistani et al.²¹ found that OCT could distinguish between multilayer interfaces between resin inlays and dental tissue, assess internal adaptation, and observe and compare the same site at different times in a long-term study. OCT could measure the MG between the teeth and the crowns and thus could be used to detect internal adhesion defects (Fig. 5). The MG of the lithium disilicate glass ceramic crown measured with stereomicroscope and OCT was evaluated. There was no significant difference between the two methods ($p = 0.736$), which indicated that the OCT method could be applied to evaluate the MG of the lithium disilicate glass ceramic crowns.

In this study, the signal intensities (small peak) at the interface between luting and tooth, and that between luting and ceramic were stronger than other areas, causing brighter areas in the images, which could be used to indicate the boundaries of different materials. The refractive index of air is $n = 1.0$, whereas the lithium disilicate glass ceramic had a refractive index of 1.55 ²⁸ and that of both the tooth and the resin composites are in the range of $n = (1.5, 1.6)$.²⁹ When light traverses the interface through two different medium, it generates refraction as well as partial reflection. The Fresnel phenomenon is the reflection of a fraction of light at an interface between two media with different refractive indices, which depends on the incidence angle and refractive index (n) contrast.¹⁹ A higher OCT signal value at the boundary was seen depending on the optical properties of the substances involved. Interpretation of the OCT signal requires knowledge of the optical properties of the media involved, and that of the interactions of light within the specimens. The range of enamel crystal caused the attenuation of the light, with weaker signal intensity at the deeper regions in the teeth. In comparison, attenuation of the light through the ceramic was less due to good optical properties of the ceramic. The Fresnel reflection can be clearly observed at the interfacial areas of teeth and luting, and that of ceramic and luting. The surface reflection was significant in the ceramic. In contrast, the surface reflection was difficult to observe well at the tooth and luting due to rough surface. As the interface between the ceramic and the luting, and that between the luting and the tooth could be easily distinguished, the MG was then measurable.

MG was the most important factor used to evaluate the success of crowns. Fransson et al.³⁰ and McLean and von Fraunhofer³¹ indicated that the clinically acceptable MG after cementation should be <150 and $120\ \mu\text{m}$, respectively. While others agreed that maximum clinically acceptable MG should be between 100 and $150\ \mu\text{m}$ with CAD/CAM ceramic blocks fabricated.^{32–34} The mean value of the MG of ceramic restorations was $56.1\ \mu\text{m}$ *in vivo* studies.³⁵ Additionally, McLean and von Fraunhofer³¹ examined the MG of 1000 fixed restorations

Table 2 The methods to assess the MG.

Methods	Measurements	Advantages	Disadvantages
Direct-view technique	Stereomicroscopy	1. Convenient 2. Brief 3. Long-term analysis	1. Identified reference points to measure may prove difficult ⁹ 2. Large standard deviations ²² 3. Projection errors ¹⁰
Cross-sectioning technique	Stereomicroscopy, scanning electron microscope	Accuracy	1. Partial sections 2. Not long-term analysis ¹²
Replica technique	A light body silicone replica	1. <i>In vitro</i> and <i>vivo</i> 2. Convenient 3. Long-term analysis	1. Each specimen partial sections 2. Mistakes in the sectioning plane can lead to overestimated measurement. ²³
Digital impression	Laser scan crown, silicone replica	Measure internal gap ²⁴⁻²⁶	Identified reference points to measure may prove difficult interpretation by profilometer ²⁷
Profile projector	Profilometer	1. Convenient 2. Brief 3. Long-term analysis	
μ -CT	μ -CT	1. Long-term analysis and comparison 2. Nondestructive 3. Provide very close sections. ⁵	1. Spend much time 2. x-ray radiation 3. Radio-opacity, low resolution

Fig. 5 Adhesion defect: there was some air (up arrow) between the enamel and the lithium disilicate glass ceramic. It was difficult to find from the surface of the crowns. (a) Enamel, (b) luting, and (c) lithium disilicate glass ceramic.

over a 5-year period and indicated that the MG $<80\text{ }\mu\text{m}$ was difficult to detect under clinical conditions. Anadioti et al.³⁶ found that the MG of E.max CAD was $74 \pm 26\text{ }\mu\text{m}$ with a laser coordinate measurement machine before cementation. Neves et al.⁵ found that the MG of E.max CAD was $39.2 \pm 8.7\text{ }\mu\text{m}$ with μ -CT before cementation. In this study, the MG of E.max CAD was $59.55 \pm 7.22\text{ }\mu\text{m}$ measured by OCT after cementation.

OCT technology was a good method to detect MG of lithium disilicate glass ceramic crowns. This technology was also potentially suitable to measure the MG with a noninvasive method in durability clinic studies. Because the crowns with chamfer had better adaptation than rounded shoulder before and after cement,³⁷ only the crowns with chamfer were used in our study. While imaging depth limitation for examination of deeper

interfaces and device miniaturization, OCT was an innovation technology for various lab and clinical applications in the dental field.

5 Conclusions

OCT was a noninvasive diagnostic imaging technique to measure the MG of lithium disilicate glass ceramic crowns. There was consistency between OCT and stereomicroscopy when measuring the MG of lithium disilicate glass ceramic crowns after cementation.

Disclosures

The authors have no conflicts of interest to disclose.

Acknowledgments

We benefited enormously from the wisdom and advice of many friends and colleagues of the Department of Stomatology, Tong Ren Hospital, to whom we would like to express our gratitude for the numerous hours and great efforts they took to collect, verify, and clean the data of this study.

References

1. F. M. Gardner, "Margins of complete crowns—literature review," *J. Prosthet. Dent.* **48**(4), 396–400 (1982).
2. M. R. Baig, K. B. Tan, and J. I. Nicholls, "Evaluation of the marginal fit of a zirconia ceramic computer-aided machined (CAM) crown system," *J. Prosthet. Dent.* **104**(4), 216–227 (2010).
3. J. R. Holmes et al., "Considerations in measurement of marginal fit," *J. Prosthet. Dent.* **62**(4), 405–408 (1989).

4. S. An et al., "Evaluating the marginal fit of zirconia copings with digital impressions with an intraoral digital scanner," *J. Prosthet. Dent.* **112**(5), 1171–1175 (2014).
5. F. D. Neves et al., "Micro-computed tomography evaluation of marginal fit of lithium disilicate crowns fabricated by using chairside CAD/CAM systems or the heat-pressing technique," *J. Prosthet. Dent.* **112**(5), 1134–1140 (2014).
6. M. Groten, S. Girthofer, and L. Probst, "Marginal fit consistency of copy-milled all-ceramic crowns during fabrication by light and scanning electron microscopic analysis in vitro," *J. Oral Rehabil.* **24**(12), 871–881 (1997).
7. P. Kohorst et al., "Marginal accuracy of four-unit zirconia fixed dental prostheses fabricated using different computer-aided design/computer-aided manufacturing systems," *Eur. J. Oral Sci.* **117**(3), 319–325 (2009).
8. A. Ortorp et al., "The fit of cobalt-chromium three-unit fixed dental prostheses fabricated with four different techniques: a comparative in vitro study," *Dent. Mater.* **27**(4), 356–363 (2011).
9. S. M. Beschnidt and J. R. Strub, "Evaluation of the marginal accuracy of different all-ceramic crown systems after simulation in the artificial mouth," *J. Oral Rehabil.* **26**(7), 582–593 (1999).
10. M. Groten et al., "Determination of the minimum number of marginal gap measurements required for practical in-vitro testing," *J. Prosthet. Dent.* **83**(1), 40–49 (2000).
11. C. A. Mitchell, M. R. Pintado, and W. H. Douglas, "Nondestructive, in vitro quantification of crown margins," *J. Prosthet. Dent.* **85**(6), 575–584 (2001).
12. B. Shearer, M. B. Gough, and D. J. Setchell, "Influence of marginal configuration and porcelain addition on the fit of In-Ceram crowns," *Biomaterials* **17**(19), 1891–1895 (1996).
13. P. Rechmann et al., "Swept source optical coherence tomography for quantitative and qualitative assessment of dental composite restorations," *Proc. SPIE* **7884**, 78840C (2011).
14. N. A. Nawafleh et al., "Accuracy and reliability of methods to measure marginal adaptation of crowns and FDPs: a literature review," *J. Prosthodont.* **22**(5), 419–428 (2013).
15. K. Imai et al., "Noninvasive cross-sectional visualization of enamel cracks by optical coherence tomography in vitro," *J. Endod.* **38**(9), 1269–1274 (2012).
16. G. C. Akar et al., "Effects of surface-finishing protocols on the roughness, color change, and translucency of different ceramic systems," *J. Prosthet. Dent.* **112**(2), 314–321 (2014).
17. P. Makishi et al., "Non-destructive 3D imaging of composite restorations using optical coherence tomography: marginal adaptation of self-etch adhesives," *J. Dent.* **39**(4), 316–325 (2011).
18. C. Sinescu et al., "Quality assessment of dental treatments using en-face optical coherence tomography," *J. Biomed. Opt.* **13**(5), 054065 (2008).
19. T. A. Bakhsh et al., "Non-invasive quantification of resin-dentin interfacial gaps using optical coherence tomography: validation against confocal microscopy," *Dent. Mater.* **27**(9), 915–925 (2011).
20. L. S. de Melo et al., "Evaluation of enamel dental restoration interface by optical coherence tomography," *J. Biomed. Opt.* **10**(6), 064027 (2005).
21. A. Turkistani et al., "Sealing performance of resin cements before and after thermal cycling: evaluation by optical coherence tomography," *Dent. Mater.* **30**(9), 993–1004 (2014).
22. K. B. May et al., "Precision of fit: the Procera AllCeram crown," *J. Prosthet. Dent.* **80**(4), 394–404 (1998).
23. P. Coli and S. Karlsson, "Fit of a new pressure-sintered zirconium dioxide coping," *Int. J. Prosthodont.* **17**(1), 59–64 (2004).
24. M. Laurent et al., "Clinical evaluation of the marginal fit of cast crowns—validation of the silicone replica method," *J. Oral Rehabil.* **35**(2), 116–122 (2008).
25. O. Moldovan et al., "Three-dimensional fit of CAD/CAM-made zirconia copings," *Dent. Mater.* **27**(12), 1273–1278 (2011).
26. E. Anadioti et al., "Internal fit of pressed and computer-aided design/computer-aided manufacturing ceramic crowns made from digital and conventional impressions," *J. Prosthet. Dent.* **113**(4), 304–309 (2015).
27. S. Pelekanos et al., "Micro-CT evaluation of the marginal fit of different In-Ceram alumina copings," *Eur. J. Esthet. Dent.* **4**(3), 278–292 (2009).
28. M. J. Heffernan et al., "Relative translucency of six all-ceramic systems. Part II: core and veneer materials," *J. Prosthet. Dent.* **88**(1), 10–15 (2002).
29. Z. Meng et al., "Measurement of the refractive index of human teeth by optical coherence tomography," *J. Biomed. Opt.* **14**(3), 034010 (2009).
30. B. Fransson, G. Oilo, and R. Gjeitanger, "The fit of metal-ceramic crowns, a clinical study," *Dent. Mater.* **1**(5), 197–199 (1985).
31. J. W. McLean and J. A. von Fraunhofer, "The estimation of cement film thickness by an in vivo technique," *Br. Dent. J.* **131**(3), 107–111 (1971).
32. F. Beuer, J. Schweiger, and D. Edelhoff, "Digital dentistry: an overview of recent developments for CAD/CAM generated restorations," *Br. Dent. J.* **204**(9), 505–511 (2008).
33. D. A. Abuelenain et al., "Comparison of stresses generated within the supporting structures of mandibular second molars restored with different crown materials: 3-D finite element analysis (FEA)," *J. Prosthodont.* **24**(6), 484–493 (2015).
34. Z. Huang et al., "Clinical marginal and internal fit of crowns fabricated using different CAD/CAM technologies," *J. Prosthodont.* **24**(4), 291–295 (2015).
35. P. Tsirogiannis, D. R. Reissmann, and G. Heydecke, "Evaluation of the marginal fit of single-unit, complete-coverage ceramic restorations fabricated after digital and conventional impressions: a systematic review and meta-analysis," *J. Prosthet. Dent.* **116**(3), 328.e2–335.e2 (2016).
36. E. Anadioti et al., "3D and 2D marginal fit of pressed and CAD/CAM lithium disilicate crowns made from digital and conventional impressions," *J. Prosthodont.* **23**(8), 610–617 (2014).
37. E. A. Tsitrou, S. E. Northeast, and R. van Noort, "Evaluation of the marginal fit of three margin designs of resin composite crowns using CAD/CAM," *J. Dent.* **35**(1), 68–73 (2007).

Wenhao Li is a dentist at the Department of Stomatology, Plastic Surgery Hospital, Chinese Academy of Medical Sciences and Peking Union Medical College, China. His research interests are tooth erosion and OCT device applied in the dental field.

Jingming Liu is a surgical dentist at the Department of Stomatology, Beijing Tong Ren Hospital, Capital Medical University, China. His research focuses on implants.

Zhenting Zhang is a prosthodontist at the Department of Prosthodontics, Capital Medical University School of Stomatology, China. His main research interest is nanomaterials for implants.