Enhancement of plasmon-induced charge separation efficiency by coupling silver nanocubes with a thin gold film

Kazutaka Akiyoshi
Koichiro Saito
Tetsu Tatsuma

SPIE.

Kazutaka Akiyoshi, Koichiro Saito, Tetsu Tatsuma, "Enhancement of plasmon-induced charge separation efficiency by coupling silver nanocubes with a thin gold film," *J. Photon. Energy* **6**(4), 042505 (2016), doi: 10.1117/1.JPE.6.042505.

Enhancement of plasmon-induced charge separation efficiency by coupling silver nanocubes with a thin gold film

Kazutaka Akiyoshi, Koichiro Saito, and Tetsu Tatsuma*

University of Tokyo, Institute of Industrial Science, 4-6-1 Komaba,
Meguro-ku, Tokyo 153-8505, Japan

Abstract. Plasmon-induced charge separation (PICS), in which an energetic electron is injected from a plasmonic nanoparticle (NP) to a semiconductor on contact, is often inhibited by a protecting agent adsorbed on the NP. We addressed this issue for an Ag nanocube-TiO₂ system by coating it with a thin Au layer or by inserting the Au layer between the nanocubes (NCs) and TiO₂. Both of the electrodes exhibit much higher photocurrents due to PICS than the electrodes without the Au film or the Ag NCs. These photocurrent enhancements can be explained in terms of PICS with accelerated electron transfer, in which electron injection from the Ag NCs or Ag@Au core-shell NCs to TiO₂ is promoted by the Au film, or PICS enhanced by a nanoantenna effect, in which the electron injection from the Au film to TiO₂ is enhanced by optical near field generated by the Ag NC. © The Authors. Published by SPIE under a Creative Commons Attribution 3.0 Unported License. Distribution or reproduction of this work in whole or in part requires full attribution of the original publication, including its DOI. [DOI: [10.1117/1.JPE.6.042505](https://doi.org/10.1117/1.JPE.6.042505)]

Keywords: plasmon-induced charge separation; localized surface plasmon resonance; electron transfer; nanoantenna effect; silver nanocube.

Paper 16058SS received May 18, 2016; accepted for publication Jul. 20, 2016; published online Aug. 9, 2016.

1 Introduction

Plasmonic light harvesting based on localized surface plasmon resonance (LSPR) of noble metal nanoparticles (NPs) has attracted much attention recently and is applied to photovoltaics and photocatalysis. There are two different ways of plasmonic light harvesting: (1) that based on a nanoantenna effect,¹ in which a metal NP entraps a photon and transfers the obtained energy to a dye molecule or semiconductor via the optical near field generated in its vicinity, and (2) that based on plasmon-induced charge separation (PICS),² in which an energetic electron is injected from a resonant NP to a semiconductor on contact. We reported PICS for the first time² and indicated that it involves electron transfer from the plasmonic NPs to the semiconductor.²⁻⁷ The electron transfer involved is explained in terms of external photoelectric effect, hot electron injection, or interfacial electron transition, and recently some groups call it plasmonic hot electron (or carrier) injection. PICS has been widely applied to photovoltaics,^{2,8-12} photocatalysis,^{2,13,14} photochromism,¹⁵⁻¹⁷ photoactuation,¹⁸ and chemical sensing.¹⁹

A wide variety of plasmonic NPs have been used for PICS such as nanospheres,²⁰ nanoplates,⁷ and halfshell arrays.²¹ NPs prepared by photocatalytic deposition² or thermal dewetting of an evaporated film⁹ are suitable for PICS because of direct contact with the semiconductor, while chemically synthesized NPs may exhibit lower charge separation efficiency since they are covered with a protective agent. In the case of Au nanorods (NRs) protected with cetyltrimethylammonium bromide in contact with a TiO₂ thin film, we addressed the issue by photoelectrochemical deposition of Au from aqueous HAuCl₄ at both ends of the NRs under UV irradiation for excitation of TiO₂.²² The Au NRs were thus converted to nanodumbbells (NDs), and NDs exhibited improved efficiency of PICS-based electron transfer to TiO₂ via the two spherical caps at both ends of NDs. Here, we propose an easier method to improve

*Address all correspondence to: Tetsu Tatsuma, E-mail: tatsuma@iis.u-tokyo.ac.jp

the PICS-based photocurrents. We use plasmonic Ag nanocubes (NCs) protected by poly(vinylpyrrolidone) (PVP) in this work. Although Ag NCs exhibit nanoantenna effects^{23–25} and various interesting optical properties,^{26–29} their PICS efficiency when they are in contact with TiO₂ is low because of the insulating PVP layer. In the present work, in order to improve the PICS efficiency, we coupled the Ag NCs simply with an evaporated Au thin film, which is coated on the Ag NCs placed on TiO₂ or coated directly on TiO₂ as the underlayer of Ag NCs.

2 Experiment

2.1 Preparation of Electrodes

Ag NCs were synthesized by the method reported by Im et al.³⁰ with slight modifications²⁸ [Fig. 1(a)]. The average edge length of the synthesized Ag NCs is about 80 nm. A transparent indium tin oxide (ITO) electrode was coated with a thin anatase TiO₂ film (60-nm thick, observed by scanning electron microscopy, SEM) by a spray pyrolysis method at 500°C from 2-propanol containing 0.028 M titanium diisopropoxide bis(acetylacetonate) as a TiO₂ precursor. The TiO₂ film was irradiated with UV light in order to make the surface sufficiently hydrophilic. The synthesized Ag NCs were drop-cast onto the TiO₂ surface (coverage $\sim 9 \times 10^8$ particles cm⁻²). If necessary, the substrate was coated with an Au film (*ca.* 5-nm thick, measured by quartz crystal microbalance) by vacuum evaporation before or after the drop-casting [Fig. 1(b)]. Thus, we prepared four different electrodes: ITO/TiO₂/Ag NC, ITO/TiO₂/Ag NC/Au, ITO/TiO₂/Au, and ITO/TiO₂/Au/Ag NC (active area = 12 × 20 mm).

2.2 Measurement of Photocurrents

One of the four electrodes was used as the working electrode. This electrode was connected to a potentiostat (SI 1280 B, Solartron) with an Ag/AgCl reference electrode and a Pt counter electrode and soaked in 0.1 M aqueous KNO₃ containing 0.5 M ethanol as an electron donor. The working electrode was polarized at +0.5 V versus Ag/AgCl and irradiated with monochromatic light (full width at half maximum = 20 nm, 5.0×10^{15} photons cm⁻² s⁻¹, and light irradiation area = 1.8 cm⁻²) using an optospectrum generator (Hamamatsu Photonics), and a steady-state photocurrent was measured at each wavelength. Virtually, the same photocurrents were observed even if the photoanode was short circuited to the counter electrode.

3 Results and Discussion

3.1 Photocurrent Responses of the ITO/TiO₂/Ag NC Electrode

Ag NCs dispersed in ethanol exhibit the main extinction peak based on dipolar LSPR at 506 nm. When an Ag NC is adsorbed onto a substrate with a high refractive index, the LSPR peak splits into two peaks due to the distal and proximal modes.²⁶ In the distal mode, electron oscillation is

Fig. 1 Scanning electron micrographs of (a) the Ag NCs and (b) the Au films. (c) Extinction spectra of the ITO/TiO₂/Ag NC, ITO/TiO₂/Ag NC/Au, ITO/TiO₂/Au, and ITO/TiO₂/Au/Ag NC electrodes in water.

localized at the top of the NC away from the substrate, and in the proximal mode, the oscillation is localized at the bottom of the NC in contact with the substrate. The Ag NCs on TiO_2 show two peaks [Fig. 1(c)], namely peak A at 456 nm due to the distal mode and peak B at 530 nm due to the proximal mode.

First, we measured photocurrent responses from the ITO/ TiO_2 /Ag NC electrode irradiated from the backside with monochromatic light of different wavelengths in the electrolyte solution. Three independently prepared electrodes were examined and the average currents were plotted against the irradiation wavelength (Fig. 2). Small anodic photocurrents were observed in the wavelength range examined (430 to 670 nm). Conduction electrons in an Ag NC oscillate in resonance with electric field oscillation of the incident light, and an electron is injected from the resonant NC to the conduction band of TiO_2 , resulting in PICS.² As a result, the anodic photocurrent flows [Fig. 3(a)]. However, the photocurrents were very low and no obvious current peaks corresponding to the distal and proximal modes were obtained. The low currents could be explained in terms of a blocking effect of insulating PVP, which covers and protects the NC surface.^{31,32} Likewise, the PVP layer should also inhibit the electron transfer from the Ag NC to TiO_2 .

Fig. 2 Photocurrent action spectra of the ITO/ TiO_2 /Ag NC, ITO/ TiO_2 /Ag NC/Au, ITO/ TiO_2 /Au, and ITO/ TiO_2 /Au/Ag NC electrodes in 0.1-M aqueous KNO_3 containing 0.5-M ethanol. Each datapoint shows the average of photocurrent responses from three independently prepared electrodes.

Fig. 3 Possible mechanisms of the photocurrents based on PICS for (a) ITO/ TiO_2 /Ag NC, (b) ITO/ TiO_2 /Au, and (c and d) ITO/ TiO_2 /Ag NC/Au electrodes [(c) PICS with accelerated electron transfer and (d) PICS enhanced by the nanoantenna effect].

3.2 Effect of a Thin Gold Coating

We therefore coated the Ag NCs on TiO_2 with a thin Au layer (*ca.* 5 nm thick) by evaporation, envisaging promotion of the electron transfer. The photocurrent responses from the ITO/ TiO_2 /Ag NC/Au electrode thus prepared were measured and are shown in Fig. 2. The Au coating greatly improved the anodic photocurrents and a broad peak was obtained at around 550 nm. This electrode showed an extinction peak at 580 nm [Fig. 1(c)]. There is a possibility that the influence of the high refractive index substrate is weakened by the Au coating and therefore the distal mode is suppressed. The photocurrent response at the peak was about 20 times higher than that without the Au coating.

We also coated the Au layer directly on TiO_2 and examined its photocurrent responses for comparison. This ITO/ TiO_2 /Au electrode also exhibited photocurrent responses that increased gradually with increasing wavelength from about 500 nm. The extinction spectrum of the Au film showed a similar trend [Fig. 1(c)]. In general, a thin Au film prepared by evaporation consists of interconnected fine Au NPs, and hence it exhibits not only the propagating surface plasmon resonance, but also LSPR.³³ Therefore, the present Au film also injects electrons into TiO_2 and exhibits photocurrents based on PICS [Fig. 3(b)]. Actually, nanoparticulate structures of 10- to 20-nm size were observed by SEM [Fig. 1(b)]. With reference to the response of this electrode, the introduction of Ag NCs under the Au thin film enhanced the photocurrents by approximately five times.

3.3 Mechanisms of the Photocurrent Enhancement

There are two possible reasons that the response from the ITO/ TiO_2 /Ag NC/Au electrode is much higher than those from the ITO/ TiO_2 /Ag NC and ITO/ TiO_2 /Au electrodes. One of them is “PICS with accelerated electron transfer” shown in Figs. 3(c) and 4(a), in which electron injection from the Ag NC or Ag@Au core-shell NC to TiO_2 is promoted by good electronic contact between the Au film and TiO_2 . The other one is “PICS enhanced by the nanoantenna effect” shown in Figs. 3(d) and 4(b), in which the electron injection from Au to TiO_2 is enhanced by optical near field generated by the Ag NC; the Ag NC absorbs light and generates optical near field in its vicinity, and then the Au film is efficiently excited by the near field (i.e., the nanoantenna effect^{23–25}) and causes PICS. In both cases, the current would be increased by increasing the amount of Ag NCs.³⁴

In order to obtain further information about the mechanisms of photocurrent enhancement, we prepared another type of electrode by drop-casting the Ag NCs onto the Au thin film coated directly on TiO_2 . The photocurrent action spectrum of the obtained ITO/ TiO_2 /Au/Ag NC electrode was similar to that of the ITO/ TiO_2 /Ag NC/Au electrode (Fig. 2), and a broad peak was observed at around 535 nm. The photocurrent enhancement factors at the peak wavelength are 23 and 5 with reference to the ITO/ TiO_2 /Ag NC and the ITO/ TiO_2 /Au electrodes, respectively. These photocurrent enhancements can also be explained in terms of both of the two possible mechanisms, namely the PICS with accelerated electron transfer and PICS enhanced by the nanoantenna effect. However, it is more likely that the Au thin film is excited by the optical near field of the NC proximal mode (i.e., the nanoantenna effect) because the PVP may also block the electron transfer from Ag NCs to the Au film.

Fig. 4 Possible mechanisms of (a) the PICS with accelerated electron transfer and (b) PICS enhanced by the nanoantenna effect.

4 Conclusions

Photocurrent responses based on PICS from the ITO/TiO₂/Ag NC/Au and the ITO/TiO₂/Au/Ag NC electrodes are much higher than those from the ITO/TiO₂/Ag NC and ITO/TiO₂/Au electrodes. These enhancements are likely due to PICS with accelerated electron transfer or PICS enhanced by the nanoantenna effect. These results would provide an easier way to improve PICS efficiency of photovoltaics, photocatalysis, and other systems with commercially available or chemically synthesized plasmonic NPs with protecting layers.

Acknowledgments

The authors are grateful to Gyu Min Kim for his help with immobilization of the NPs. This work was supported in part by a Grant-in-Aid for Scientific Research (Nos. 16H02082 and 16K14017) from the Japan Society for the Promotion of Science.

References

1. H. A. Atwater and A. Polman, "Plasmonics for improved photovoltaic devices," *Nat. Mater.* **9**, 205–213 (2010).
2. Y. Tian and T. Tatsuma, "Mechanisms and applications of plasmon-induced charge separation at TiO₂ films loaded with gold nanoparticles," *J. Am. Chem. Soc.* **127**, 7632–7637 (2005).
3. N. Sakai et al., "Plasmon resonance-based generation of cathodic photocurrent at electro-deposited gold nanoparticles coated with TiO₂ films," *ChemPhysChem* **10**, 766–769 (2009).
4. Y. Tian and T. Tatsuma, "Plasmon-induced photoelectrochemistry at metal nanoparticles supported on nanoporous TiO₂," *Chem. Commun.* **16**, 1810–1811 (2004).
5. Y. Takahashia and T. Tatsuma, "Electrodeposition of thermally stable gold and silver nanoparticle ensembles through a thin alumina nanomask," *Nanoscale* **2**, 1494–1499 (2010).
6. T. Yamaguchi et al., "Photoelectrochemical responses from polymer-coated plasmonic copper nanoparticles on TiO₂," *Chem. Lett.* **41**, 1340–1342 (2012).
7. E. Kazuma and T. Tatsuma, "In-situ nanoimaging of photoinduced charge separation at the plasmonic Au nanoparticle-TiO₂ interface," *Adv. Mater. Interfaces* **1**, 1400066 (2014).
8. K. Yu, N. Sakai, and T. Tatsuma, "Plasmon resonance-based solid-state photovoltaic devices," *Electrochemistry* **76**, 161–164 (2008).
9. Y. Takahashi and T. Tatsuma, "Solid state photovoltaic cells based on localized surface plasmon-induced charge separation," *Appl. Phys. Lett.* **99**, 182110 (2011).
10. Y. K. Lee et al., "Surface plasmon-driven hot electron flow probed with metal-semiconductor nanodiodes," *Nano Lett.* **11**, 4251–4255 (2011).
11. S. Mubeen et al., "Plasmonic photosensitization of a wide band gap semiconductor: converting plasmons to charge carriers," *Nano Lett.* **11**, 5548–5552 (2011).
12. P. Reineck et al., "A solid-state plasmonic solar cell via metal nanoparticle self-assembly," *Adv. Mater.* **24**, 4750–4755 (2012).
13. E. Kowalska, R. Abe, and B. Ohtani, "Visible light-induced photocatalytic reaction of gold-modified titanium(IV) oxide particles: action spectrum analysis," *Chem. Commun.* 241–243 (2009).
14. A. Tanaka, K. Hashimoto, and H. Kominami, "Preparation of Au/CeO₂ exhibiting strong surface plasmon resonance effective for selective or chemoselective oxidation of alcohols to aldehydes or ketones in aqueous suspensions under irradiation by green light," *J. Am. Chem. Soc.* **134**, 14526–14533 (2012).
15. Y. Ohko et al., "Multicolor photochromism of TiO₂ films loaded with Ag nanoparticles," *Nat. Mater.* **2**, 29–31 (2003).
16. E. Kazuma and T. Tatsuma, "Photoinduced reversible changes in morphology of plasmonic Ag nanorods on TiO₂ and application to versatile photochromism," *Chem. Commun.* **48**, 1733–1735 (2012).
17. I. Tanabe and T. Tatsuma, "Plasmonic manipulation of color and morphology of single silver nanospheres," *Nano Lett.* **12**, 5418–5421 (2012).

18. T. Tatsuma, K. Takada, and T. Miyazaki, "UV light-induced swelling and visible light-induced shrinking of a TiO₂-containing redox gel," *Adv. Mater.* **19**, 1249–1251 (2007).
19. T. Tatsuma et al., "Direct output of electrical signals from LSPR sensors on the basis of plasmon-induced charge separation," *Chem. Commun.* **51**, 6100–6103 (2015).
20. K. Yu, Y. Tian, and T. Tatsuma, "Size effects of gold nanoparticles on plasmon-induced photocurrents of gold-TiO₂ nanocomposites," *Phys. Chem. Chem. Phys.* **8**, 5417–5420 (2006).
21. L. Wu, H. Nishi, and T. Tatsuma, "Plasmon-induced charge separation at two-dimensional gold semishell arrays on SiO₂@TiO₂ colloidal crystals," *APL Mater.* **3**, 104406 (2015).
22. Y. Katagi, E. Kazuma, and T. Tatsuma, "Photoelectrochemical synthesis, optical properties and plasmon-induced charge separation behaviour of gold nanodumbbells on TiO₂," *Nanoscale* **6**, 14543–14548 (2014).
23. S.-W. Baek et al., "Au@Ag core-shell nanocubes for efficient plasmonic light scattering effect in low bandgap organic solar cells," *ACS Nano* **8**, 3302–3312 (2014).
24. T. Kawawaki et al., "Efficiency enhancement of PbS quantum dot/ZnO nanowire bulk-heterojunction solar cells by plasmonic silver nanocubes," *ACS Nano* **9**, 4165–4172 (2015).
25. K. Leonard et al., "Enhanced photoelectrochemical response of polythiophene photoelectrodes with controlled arrays of silver nanocubes," *J. Phys. Chem. C* **119**, 8829–8837 (2015).
26. L. J. Sherry et al., "Localized surface plasmon resonance spectroscopy of single silver nanocubes," *Nano Lett.* **5**, 2034–2038 (2005).
27. A. Moreau et al., "Controlled-reflectance surfaces with film-coupled colloidal nanoantennas," *Nature* **492**, 86–89 (2012).
28. K. Saito and T. Tatsuma, "Asymmetric three-way plasmonic color routers," *Adv. Opt. Mater.* **3**, 883–887 (2015).
29. K. Saito and T. Tatsuma, "A transparent projection screen based on plasmonic Ag nanocubes," *Nanoscale* **7**, 20365–20368 (2015).
30. S. H. Im et al., "Large-scale synthesis of silver nanocubes: the role of HCl in promoting cube perfection and monodispersity," *Angew. Chem., Int. Ed.* **117**, 2192–2195 (2005).
31. M. Luo et al., "Facile removal of polyvinylpyrrolidone (PVP) adsorbates from Pt alloy nanoparticles," *J. Mater. Chem. A* **3**, 2770–2775 (2015).
32. Z. Niu and Y. Li, "Removal and utilization of capping agents in nanocatalysis," *Chem. Mater.* **26**, 72–83 (2014).
33. R. Gupta, M. J. Dyer, and W. A. Weimer, "Preparation and characterization of surface plasmon resonance tunable gold and silver films," *J. Appl. Phys.* **92**, 5264–5270 (2002).
34. T. Kawawaki, Y. Takahashi, and T. Tatsuma, "Enhancement of PbS quantum dot-sensitized photocurrents by plasmonic gold nanoparticles," *J. Phys. Chem. C* **117**, 5901–5907 (2013).

Kazutaka Akiyoshi is a PhD candidate in University of Tokyo, Japan. He received his BSc degree from Tokyo University of Science in 2014 and MSc from University of Tokyo in 2016. His research focuses mainly on development of photoelectrochemical devices based on plasmonic nanoparticles.

Koichiro Saito is a PhD candidate in University of Tokyo, Japan. He received his BSc in 2013 and MSc in 2015 degrees from University of Tokyo. His research focuses mainly on fabrication and photo-manipulation of plasmonic nanomaterials and application to photonic materials and devices.

Tetsu Tatsuma is a professor at University of Tokyo, Japan. He received his BSc in 1988, MSc in 1990, and PhD in 1993 degrees in electrochemistry from University of Tokyo. His current research interests include electrochemistry and plasmonics, in particular mechanistic analysis of plasmon-induced charge separation and its application to photovoltaics, photocatalysis, photochromism, sensors, and actuators.